

Product description

Enkadrain 5006H/M200PP is a light and flexible geocomposite matting, made up of a three-dimensional polypropylene monofilament drainage core. The matting is thermally pre-formed in a v-shape configuration, making it optimally pressure resistant. In the machine direction (MD) the matting has the highest discharge capacity. For this reason Enkadrain 5006H/M200PP should be installed preferably with the machine direction parallel to the expected flow direction. Due to the basic filament structure a flow between the individual channels is possible.

Enkadrain 5006H/M200PP is manufactured in 5 m wide lanes. The drain is covered on both sides with a mechanically bonded polypropylene nonwoven filter. The filters are bonded to the drainage core by means of stitching. The seams of the stitching are parallel to the machine direction. Each of the nonwoven filters extend 100 mm to one side of the core in opposite directions. This ensures that the joint is covered when lanes of Enkadrain are layed adjacent to one another.

Application

Enkadrain 5006H/M200PP has a high discharge capacity so that the geocomposite can be used to replace mineral drain and filter layers in the civil engineering and building industry. Enkadrain 5006H/T110PP can also be used as drainage layer in the cappings of landfills.

To avoid damage caused by UV radiation or wind we advise to cover Enkadrain immediately, but at least 4 weeks after installation.

Performances

Properties of the composite

Applied stress in kPa	Hydraulic gradient i in -	Water flow capacity in-plane* $Q_{\text{stress/gradient}}$ in $l/(s \cdot m)$ **		
		Mean value	Tolerance value	
20	1.0	1.1	-0.3	EN ISO 12958

* Test results by Colbond Geosynthetics Laboratory according to EN ISO 12958, opt. R/F.
Soil pressure against one filter side was simulated by a foam layer.

** $l/(s \cdot m) = 10^{-3} m^2/s$

Hydraulic properties of the filter M200PP

		Mean value	Tolerance value	
Water permeability, V_{H50}	mm/s	80	- 10	EN ISO 11058
Opening size	μm	90	+/- 30	EN ISO 12956

Mechanical properties of the filter M200PP

		Mean value	Tolerance value	
Polymer		PP		
Mass per unit area	g/m^2	200	- 10	EN 965
Thickness	mm	2.0	- 0.2	EN 964-1
Tensile strength MD	kN/m	8.5	- 1.5	EN 10319
Tensile strength CMD	kN/m	13.0	- 1.5	EN 10319
Elongation at break MD	%	60	- 10	EN 10319
Resistance to static puncture	kN	1.9	- 0.3	EN 12236
Dynamic perforation resistance	mm	20	+ 5	EN 918

Mean value + tolerance value correspond to the 95% confidence level.

Dimensions and weights

Enkadrain Wide	Mattings					Rolls		
	Thickness	Weight	Width	Length	Area	Ø	Length	Gross-weight
Type	mm	g/m ²	m	m	m ²	m	m	kg
5006H/5-2s/M200PP	8	800	5.00	100	500	1.05	5.30	415

Individual values may vary from above mentioned data.

Quality Assurance



The Quality Management System of Colbond Geosynthetics, at Arnhem (development and sales) and Oberburg (production), has been approved by Lloyd's Register Quality Assurance Limited for the ISO 9001:2000 quality management system standard (Certificate No. 935136).



0799-CPD

Enkadrain 5006H/M200PP is CE-certified by an independent notified body (0799-CPD).

Colbond Geosynthetics, P.O. Box 9600, 6800 TC Arnhem, the Netherlands
Phone: +31 26 366 4600 • Fax: +31 26 366 5812
geosynthetics@colbond.com • www.colbond.com

The information set forth in this brochure reflects our best knowledge at the time of issue. The brochure is subject to change pursuant to new developments and findings, and a similar reservation applies to the properties of the products described. We undertake no liability for results obtained by usage of our products and information.