



# PRODUCT DATA



Date: 20 November 2005

Information Sheet No.: ZE0449

## **EVO-STIK STICKS LIKE SH\*T A SINGLE-PART, MS POLYMER ADHESIVE**

Evo-Stik Sticks Like Sh\*T is a high performance, single component, moisture curing, Modified Silane (MS) Polymer based. It will bond most surfaces even if both are impervious. The product will bond damp surfaces and may even be used underwater. It has very low odour, cures to form a hard elastic rubber, with almost no shrinkage and low hazard; it does not contain any water or solvent, making it ideal for bonding foam polystyrene sheets. When fully cured the product may be painted with most types of paints.

### **APPLICATIONS**

- Bonds to most surfaces including wood, concrete, brick, plaster, glass, ceramics, metals, rigid pvc, grp, insulation boards and foam polystyrene.
- Bonds panels, signs, mirrors, wallboards, skirtings etc. of the above surfaces.

### **LIMITATIONS**

- Will not bond Polythene, polypropylene & Teflon. It should not be used on bitumen contaminated surfaces.
- Do not use to bond safety mirrors or very large heavy mirrors without some mechanical support.

### **METHOD OF USE**

### **PREPARATION**

- Any loose or weak layers on the surface must be removed.
- Surfaces must be clean and preferably dry.
- Surfaces that are damp **MUST** be checked for weak or loose matter on the surface that the damp might hide.

### **APPLICATION**

- Apply parallel beads of adhesive to one of the surfaces, Then bring the two surfaces together, within 10 minutes

- 5mm diameter. Beads are generally sufficient. For close fitting surfaces these may be reduced to 3mm.
- The degree of separation of the beads of Evo-Stik Sticks Like Sh\*T will depend upon the rigidity and weight of the panel, board or sign being bonded. If beads are separated by more than 200mm a perimeter bead should be applied.
- For rigid sheets 100 -150mm separation between beads is generally sufficient for high loading, but may be increased if the load is low (such a wallboards and foam polystyrene) where 200 - 500mm is acceptable.
- For less rigid boards the separation may need to be quite small and it is important to choose the correct bead size.

### **CLEANING**

1. Uncured product may be removed using cloths lightly moistened with white spirit, after carefully scraping off the bulk.
2. Cured product requires mechanical removal.



# PRODUCT DATA



Date: 20 November 2005

Information Sheet No.: ZE0449

- COVERAGE:** 44 metres of 3mm diameter bead. Per 290ml  
14 metres of 5mm diameter bead. Per 290ml
- SHELF LIFE:** 18 months from the date of manufacture.
- STORAGE:** Store, in dry conditions, between 5°C & 25°C.
- COLOUR:** Warm White.
- PACKAGING:** Code: 663589 290ml cartridges x12
- HEALTH & SAFETY:** Available separately in file named as the packaging code above.

## TYPICAL CHARACTERISTICS

- Constitution:** Moisture curing MS Polymer system
- Skin time:** About 5-15 minutes at 25°C
- Full cure:** 17-24 hours
- Colour:** Warm White
- Density (SG):** 1.5
- Shore A hardness:** 50-55
- Tensile strength:** 1.5-1.8 MPA
- Elongation at break:** 200-300%
- Movement accommodation:** Up to ± 12% of the mean joint width
- Shrinkage:** Less than 3%
- Water:** Excellent resistance.
- Oil & Petrol:** Good resistance.
- Chemicals:** Good resistance.
- Abrasion:** Good resistance.
- Paint-ability:** Cured product may be overpainted with most types of paints. In some rare cases the surface may retain slight tack, which often, another coat of the paint will cure.
- Transport:** Not designated as hazardous.

Sales & Technical contacts at Bostik	Telephone	Facsimile	Email addresses
Sales	01785 272700	01785 241818	<a href="mailto:customer.service@bostik.com">customer.service@bostik.com</a>
Technical advice	01785 272727	01785 272867	<a href="mailto:technical.service@bostik.com">technical.service@bostik.com</a>
Technical Data & COSHH (MSDS) sheets	01785 272827	01785 212962	<a href="mailto:gatehouse@bostik.com">gatehouse@bostik.com</a>

This Product Data Sheet covers just one of a large range of products supplied by Bostik Limited. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This Product Data Sheet supersedes all previous technical information on this product, and users of it are cautioned to ensure that it is the current issue. Destroy all previous Product Data Sheets, and if any doubt, contact Bostik Limited, quoting the code number in the top right hand corner on the front of this document. This leaflet is for general guidance only and may contain inappropriate information under particular conditions of use. The company cannot accept any responsibility for loss or damage that may result from the use of this information, due to the possibility of variations of processing or working conditions and of workmanship outside our control. Users are advised to confirm the suitability of this product by their own tests.